

Multi Primer is a ready-to-use adhesive adhesion promoter for use with our butyl and bituplast strips, tapes and membranes, for our Fasatan®-Fix-System and adhesive pastes Fasatan® TFS and TFU on varying building surfaces such as plaster, concrete, gas-aerated concrete, brick, sand-lime brick, hard PVC and various sheet metals.

Multi Primer corresponds to the requirements of the AgBB-schema 2018 (28 days) – requirements to the emission behaviour stated by the German board for health risk assessment of building products.

Technical data:

Basis	synthetic rubber and synthetic resin, dissolved in flammable solvents
Colour	black
Temperature resistance	- 30 °C to + 90 °C
max. Processing temperature	+ 25 °C
Viscosity at + 20 °C	900 mPa·s
Flashpoint	< 0 °C
Density at + 20 °C	0.84 g / cm ³
Primer film	elastic when dry
Consumption	100 – 200 g / m ² (dependent on surface)
Cleaning of equipment	Clean immediately after use with Fasatan® cleaner / thinner

Processing notes:

Surface: Surface may not be oxidised and must be clean, dry, smooth, weight-bearing and free of loose elements in addition to dust, grease, ice, frost and dew. Absorbent surfaces may be slightly moist (but no running water or water film), unless it is no longer possible to dry them out after applying the Multi Primer.

Check before use to ensure that the surface is compatible with the Multi Primer.

It is possible to use the Multi Primer on first opening provided that it is sufficiently liquid and can be applied cleanly and sparingly to the surface before being cleanly absorbed.

Sharp or pointed uneven patches must be eliminated. Small holes, defects and grooves must be filled with a mineral repair grout before priming takes place.

Processing: The Multi Primer should be well-shaken and stirred before use! It is ready-to-use and should not be diluted or mixed with other products.

The Multi Primer should be applied to the complete surface in one step with a roller or brush. Ensure the Multi Primer is applied evenly. Ensure undercoat of Multi Primer is completely dry and aired before using our strips or tapes (i.e. primer should not run when touched). It is crucial to check that surface is dry before mounting our strips or tapes.

To test, stick a small section of the strip or tape onto the surface, press on firmly and then tear off. If the undercoat peels off again, the adhesive process is not yet complete. If this is the case, the strip or tape should be mounted at a later point. The adhesive process can be considered complete when the strip or tape can only be removed from the surface using considerable force. As a clue for the drying time 30 can be valid – 40 minutes with 20 °C. This is depending on the composition and the temperature of the subsoil and can be extended at deep temperatures considerably.

The time of the application up to covering the Primers should not cross 4 hours. Within this time neither pollutions nor humidity may reach the Primer.

Minimum processing temperature: From + 5 °C on as a primer for our Butyl adhesive tapes, for our Bituplast repair tapes and Fasatan®-Fix as well as for our adhesive pastes Fasatan® TFS and TFU. From - 10 °C on in combination with our Bituplast® AW and our Winflex Optima sealing tapes (conditions for substrate and processing conditions must be absolutely observed). These values refer to the surface temperature of the component (temperature of the surface to be adhered).

Storage:

Store in sealed original containers, dry, at temperatures between + 15 °C and + 25 °C without direct exposure to sun light. Shelf life at least 12 months from date of producing on in unopened, tightly closed original vessel.

Safety guidelines:

- Multi Primer is flammable and must be kept away from fire and flammable sources.
- Multi Primer should not be used as an undercoat for solvent-sensitive surfaces such as PS-foam and softened PVC.
- For further information on handling, refer to the Material Safety Data Sheet.

Attention! Important Note:

Above information are based on best present knowledge of current technology, but do not guarantee faultless processing of our products. The information is based on practical results of our tests, but is not binding and does not constitute warranties of characteristics in terms of Federal Supreme Court jurisdiction. Our information does not constitute a legally binding assurance of certain properties or suitability for a specific purpose. Supplementary information by our specialists are merely recommendations, for which no liability is accepted.

Due to the many possible applications of our products, we recommend subjecting the project to a thorough suitability test on original materials before release for further application.

Since our information are non-binding we do not warranty their correctness. For this reason we accept no liability for possible improper processing based on information submitted by our employees.

This technical data sheet replaces all previous versions and is valid until a new version is issued, or until Dec. 31, 2024. Please request the latest version after Jan. 01, 2025.

Dr. Hermann, Anwendungstechnik / Application Technology, Gingen / Fils